

Cross Reference of High Performance Alloy

UNS & Grade		W.N. & DIN		GB/T	
N10001	Hastelloy B			NS3201	NS321
N10665	Hastelloy B-2	2.4617	NiMo28	NS3202	NS322
N10675	Hastelloy B-3	2.4600	NiMo29Cr	NS3203	NS323
N10002	Hastelloy C			NS3303	NS333
N06455	Hastelloy C-4	2.4610	NiMo16Cr16Ti	NS3305	NS335
N06022	Hastelloy C-22	2.4602	NiCr21Mo14W	NS3308	NS338
N10276	Hastelloy C-276	2.4819	NiMo16Cr15W	NS3304	NS334
N06200	Hastelloy C-2000	2.4675	NiCr23Mo16Cu	NS3405	NS345
N06030	Hastelloy G-30	2.4603	NiCr30FeMo	NS3404	NS344
N06035	Hastelloy G-35	2.4643	NiCr33Mo8		
N06002	Hastelloy X	2.4665	NiCr22Fe18Mo	GH3536	GH536
N06600	Inconel 600	2.4816	NiCr15Fe	NS3102	NS312
N06601	Inconel 601	2.4851	NiCr23Fe	NS3103	NS313
N06617	Inconel 617	2.4663	NiCr23Co12Mo		
N06625	Inconel 625	2.4856	NiCr22Mo9Nb	NS3306	NS336
N06690	Inconel 690	2.4642	NiCr29Fe	NS3105	NS315
N09706	Inconel 706			GH2706	GH706
N07718	Inconel 718	2.4668	NiCr19Fe19Nb5Mo3	GH4169	GH169
N07750	Inconel X-750	2.4669	NiCr15Fe7TiAl	GH4145	GH145
N08800	Incoloy 800	1.4876	X10NiCrAlTi32-21	NS1101	NS111
N08810	Incoloy 800H	1.4958	X5NiCrAlTi31-20	NS1102	NS112
N08811	Incoloy 800HT	1.4959	X8NiCrAlTi32-21		
N08825	Incoloy 825	2.4858	NiCr21Mo	NS1402	NS142
N09925	Incoloy 925	2.4852	NiCr20FeMo3TiCuAl		
N09945	Incoloy 945				
N08020	Incoloy 20	2.4660	NiCr20CuMo	NS1403	NS143
N08028	Incoloy 28	1.4563	X1NiCrMoCu31-27-4		00Cr27Ni31Mo3Cu
N08330	Incoloy 330	1.4886	X10NiCrSi35-19		
N08926	Incoloy 25-6Mo	1.4529	X1NiCrMoCuN25-20-7		
S66286	Incoloy A-286 Grade 660	1.4980	X6NiCrMoVB25-15-2	GH2132 06Cr15Ni25Ti2MoAlVB	GH132 0Cr15Ni25Ti2MoAlVB
R30188	Haynes 188			GH5188	GH188
R30605	Haynes 25			GH5605	GH605
N06230	Haynes 230	2.4733	NiCr22W14Mo		GH230
N08120	Haynes HR-120	2.4854	NiFe33Cr25Co	GH3922	GH3922
N04400	Monel 400	2.4360	NiCu30Fe		
N05500	Monel K-500	2.4375	NiCu30Al		

You could send email to sales@huishih.com for more information.

Copyright HUISHIH Alloy Corporation.

The data contained in this publication is for informational purposes only and may be revised at any time without prior notice.

Cross Reference of High Performance Alloy

UNS & Grade		W.N. & DIN		GB/T	
C71500	CuNi 70/30	2.0882	CuNi30Mn1Fe	CW354H, BFe30-0.7	B30
N02200	Nickel 200	2.4066	Ni 99.2		
N02201	Nickel 201	2.4068	LC-Ni 99		
K93120	Maraging C300				
N07080	Nimonic 80A	2.4952	NiCr20TiAl	GH4080A	GH80A
N09901	Nimonic 901	2.4662	NiFe35Cr14MoTi	GH2901	GH901
	Refractaloy 26 (R-26)				GH26
K94610	Kovar Alloy	1.3981	NiCo 29 18		4J29
K93603	Invar Alloy	1.3912	Ni 36		4J36
K93500	Super-Invar Alloy				4J32

You could send email to sales@huishih.com for more information.

Copyright HUISHIH Alloy Corporation.

The data contained in this publication is for informational purposes only and may be revised at any time without prior notice.